

PORCELAINED STONEWARE WITH MASS COLOURING

SO 13006 Class

Symbols	Features	Unit of mesurement	mean value	Fixed value	Test method
	Dimensions-Lenght and widht	%	+/- 0,4	+/- 0,6 max	UNI EN ISO 10545-2
	Side straightness	%	+/- 0,4	+/- 0,5 max	UNI EN ISO 10545-2
	Corner squareness	%	+/- 0,4	+/- 0,6 max	UNI EN ISO 10545-2
	Flatness	%	+/- 0,4	+/- 0,5 max	UNI EN ISO 10545-2
	Thickness	%	+/- 5,0	+/- 5,0 max	UNI EN ISO 10545-2
	Water absorption	%	< 0,2	≤ 0,5	UNI EN ISO 10545-3
	Breaking strenght	N	> 1600	≥ 1300 se Spess. ≥ 7,5 ≥ 700 se Spess. ≤ 7,5	UNI EN ISO 10545-4
	Modulus of rupture	N/mm ²	> 40	≥ 35	UNI EN ISO 10545-4
	Coeff. of linear thermal expansion	°MK (-1)	7,0	available method	UNI EN ISO 10545-8
	Thermal shock resisyance	-	resist	available method	UNI EN ISO 10545-9
	Stain resistance	-	≥ 3	3 MIN	UNI EN ISO 10545-14
	Resistance to chemical products	-	conform	MIN GB	UNI EN ISO 10545-13
	Resistant to acids and low concentration bases	-	GLA	available method	UNI EN ISO 10545-13
	Frost resistance	-	resist	request	UNI EN ISO 10545-12
	Colour stability	-	stable	available method	DIN 51094




RECOMMENDEND INSTALLATION

1/2 NO



1/4 YES



ATTENTION

LAYING RECTIFIED ITEMS, ALWAYS USE A 2 MM JOINT.